

| | | |
|---|--|------------|
| Article code: 48430 | TESSUTO JACQ.GIANO 4843 | (52114910) |
| Composition | 75%CO 20%PC 5%A.F. | |
| Width | 140,00 | |
| Weight / lmt | 0,70 | |
| Wash / Iron |  | |
| Shrinkage % | 2,00 | |
| Abrasion resistance (UNI EN ISO 12947-2:2000) (Martindale abrasion machine) | 30000 | |
| Back-ground | End-point rubs | |
| Design | | |
| Determination of fabric propensity to surface fuzzing and to pilling (ISO 12945-2:2002) | | |
| Pilling - Assessment at 5000 rubs | 3 | |
| Colour Fastness to Light (Xenotest) (UNI EN ISO 105 B02:2001) | 4/5 | |
| Colour Fastness to Dry Crocking (UNI EN ISO 105 X12:03) | | |
| Warp | 3/4 | |
| Weft | 3/4 | |
| Colour Fastness to Wet Crocking (UNI EN ISO 105 X12:03) | | |
| Warp | 3 | |
| Weft | 3 | |
| Determination of the slippage resistance of yarns at seam in woven fabrics (ISO 13936-1:2004) | | |
| Weft/Warp: | Slippage 6 mm | N 200,00 |
| Warp/Weft: | | N 200,00 |
| Cigarette Test (BS 5852:1990) | | |
| Match Test (BS 5852:P.2) | | |