

EnzodegliAngiuoni

Code LINEN BLEND 11987

Composition 55% Lino 45% Cotone

Standard Width cm 140

Real Width cm 150 **g*m²** 330

Rel. 0

g*m 495

date 23/01/2007

Signature Ilaria Luraschi

Characteristic	Test method	Values	Unit of meas.	Upd. date	Source
Colour fastness					
to light	BS EN ISO 105-B02:1999	4 - 6	blue scale	12/03/08	EDA Lab.
to dry rubbing	BS EN ISO 105-X12:2002	3 - 5	grey scale	12/03/08	EDA Lab.
to wet rubbing	BS EN ISO 105-X12:2002	2/3 - 5	grey scale	12/03/08	EDA Lab.
to abrasion	BS EN ISO 12947/4:1999	4/5	grey scale	12/03/08	EDA Lab.
to mechanical washing	BS EN ISO 105-C06:1997	4/5 - 5	grey scale	12/03/08	EDA Lab.
to dry cleaning	BS EN ISO 105-D01:1995	5	grey scale	12/03/08	EDA Lab.
to hand washing	BS EN ISO 105-C01:1992	4/5 - 5	grey scale	12/03/08	EDA Lab.
Dimensional change to washing					
to domestic washing	BS EN ISO 6330:2001	- 3	%	23/01/07	EDA Lab.
to cold-water immersion	BS EN ISO 6330:2001	- 2.5	%	23/01/07	EDA Lab.
to dry cleaning	BS EN ISO 3175/1:1998	- 1.5	%	29/01/07	EDA Lab.
Physical-mechanical characteristics					
seam slippage	BS EN ISO 13936/2:2004	4	mm	23/01/07	EDA Lab.
tear strength	BS EN ISO 13937/3:2002	38	N.	23/01/07	EDA Lab.
tensile strength	BS EN 13934/1:1999	872	N.	23/01/07	EDA Lab.
		c.v. 8%			
elongation strength	BS EN 13934/1:1999	12	%	23/01/07	EDA Lab.
		c.v. 5%			
pilling	BS EN 12945-2:2002	4	degree	23/01/07	EDA Lab.
abrasion resistance	BS EN 12947/2:1999	30.000	rot.	23/01/07	EDA Lab.
cigarette test	BS5852 part 1:(1990)	PASS		26/01/09	West Yorkshire

Care Instruction



IMPORTANTE

non usare detersivi che contengono ossidanti o candeggianti ottici

IMPORTANT

the washing powder should not contain oxidizing agents or brightening agents

WICHTIG

das Reinigungsmittel muss kein Oxydationsmittel oder Aufhellmittel enthalten

IMPORTANT

le détergent ne doit pas contenir aucun agent d'oxidation ou agent blanchissant

SPECIAL TREATMENT