

Article code: 48600	TESSUTO JACQ.OBAN 4860	(52114910)
Composition	75%CO 20%PC 5%A.F.	
Width	140,00	
Weight / lmt	0,69	
Wash / Iron		
Shrinkage %	2-3,00	
Abrasion resistance (UNI EN ISO 12947-2:2000) (Martindale abrasion machine)	25000	
Back-ground	End-point rubs	
Design		
Determination of fabric propensity to surface fuzzing and to pilling (ISO 12945-2:2002)		
Pilling - Assessment at 5000 rubs	3	
Colour Fastness to Light (Xenotest) (UNI EN ISO 105 B02:2001)	4/5	
Colour Fastness to Dry Crocking (UNI EN ISO 105 X12:03)		
Warp	3/4	
Weft	3/4	
Colour Fastness to Wet Crocking (UNI EN ISO 105 X12:03)		
Warp	3	
Weft	3	
Determination of the slippage resistance of yarns at seam in woven fabrics (ISO 13936-1:2004)		
Weft/Warp:	Slippage 6 mm	N 200,00
Warp/Weft:		N 200,00
Cigarette Test (BS 5852:1990)	S	
Match Test (BS 5852:P.2)	N	